

# BONDERITE L-GP MS 401N ACHESON

Known as Dag MS-401N  
July 2015

## PRODUCT DESCRIPTION

BONDERITE L-GP MS 401N ACHESON provides the following product characteristics:

<b>Technology</b>	Lubricant
<b>Product Type</b>	Yttriumoxide dispersion in solvent
<b>Application</b>	Protective coating

BONDERITE L-GP MS 401N ACHESON is a silk screen printable stop-off for use in the fabrication of titanium components by the superplastic forming/diffusion bonding process.

BONDERITE L-GP MS 401N ACHESON contains yttrium oxide and a low carbon residue binder in solvent.

Yttrium oxide is inert with respect to titanium, thus preventing the formation of alpha case in the titanium surface.

Its particle size is selected and controlled to reduce resistance to breakthrough.

The low carbon residue binder is chosen to give minimum carbon inclusion in the titanium surface.

BONDERITE L-GP MS 401N ACHESON contains no halogens.

BONDERITE L-GP MS 401N ACHESON is designed as a ready for use product for application by silk screen printing.

### Benefits:

- Inert to titanium.
- Reduced breakthrough pressure.
- Minimum carbon inclusion in titanium surface.
- No Boron induced corrosion fractures.
- No halogen induced stress fractures.

### Application Areas:

For use in the fabrication of titanium components by the superplastic forming/diffusion bonding process.

## TECHNICAL DATA

### (as supplied)

Appearance	Creamy liquid
Colour:	white
Total solids (120°C), %	~66.0
Active solids (600°C), %	~53.5
Viscosity, cPs (Brookfield)	~8,000
Carrier	Butyl Glycol Acetate
Diluent	Butyl Glycol Acetate

## DIRECTION OF USE

### Preliminary Statement:

Prior to application it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

### Method of Use:

Components should be thoroughly degreased before use. Although BONDERITE L-GP MS 401N ACHESON does not settle a small amount of solvent may bleed from the surface during storage, therefore the product should be thoroughly stirred prior to use.

BONDERITE L-GP MS 401N ACHESON is supplied ready for use by silk screen printing.

Apply in a well ventilated area.

Allow coatings to dry thoroughly.

### Dilution

BONDERITE L-GP MS 401N ACHESON should not require dilution. Occasionally, to suit a particular application, or if solvent has been lost due to evaporation, it may be necessary to dilute the product. In this case use only Butyl Glycol Acetate as a diluent.

### Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

**Hazards identification**  
**Transport information**  
**Regulatory information**

### Storage:

Recommended Storage Temperature, °C	5 to 40
Shelf life, months (in unopened original packaging)	12

Store in a dry place.

Reseal containers after use to avoid contamination.

**ADDITIONAL INFORMATION****Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

## Reference 0.0