

TEROSON EP 1401

July 2022

PRODUCT DESCRIPTION

Technology	Epoxy Resin
Product type	Structural Foam
Additional Information	2-component solvent free

TEROSON EP 1401 is a solvent free, slightly expanding, two component adhesive, based on flexibilised and toughened Epoxy Resins. The material cures at room temperature by reaction of component A and B. By heating up to a temperature above 70°C the material starts to foam. Dependent on the geometry and amount of material, the degree of foam can vary.

Application Areas:

TEROSON EP 1401 contains hollow microspheres, by which stiffness, strength and fatigue limit is increased. TEROSON EP 1401 is used as reinforcement e.g. for cavities, metal sheets and structural parts. Observe OES instructions.

TECHNICAL DATA

(Typical Test Results)

PART A

Base	Epoxy Resin
Colour	dark grey
Odour	characteristic
Density	approx. 0.8 g/cm ³

PART B

Base	Amine
Colour	white/ light grey
Odour	of amines
Density	approx. 0.6 g/cm ³

Mixing ratio A:B by volume	2:1
-------------------------------	-----

Mixture (PART A+B)

Colour	grey
Odour	no smell after curing
Processing time at 23 °C, 50% RH	90 min(s)
Density (cured) 24 hr(s) at 98 % rh and 40 °C	approx. 0.7 g/cm ³ <0.5 % weight gain
Water absorption	
Compressive strength	15 to 20 MPa
E-Modulus	700 MPa
Poisson ratio	0.22 to 0.26
Volume change (depending on the curing	0 to 30 %

conditions/ volume / geometry)
In service temperature -40 to 90 °C

PRELIMINARY STATEMENT

Prior to use it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Pretreatment:

The surfaces must be dry and free of oil, grease and dust. For pretreatment of the application area / surface use TEROSON VR 10.

Application:

TEROSON EP 1401 is processed from universal cartridges with manual application tools (dispenser driven by hand, air pressure or battery). Only use dispensers that are equipped with a piston rod. **If necessary, the cartridge can be preheated to 60°C.** Prior to screwing the static mixer, a small amount of the material should be pressed out to ensure that both components are passed on simultaneously. To ensure proper mixing, discard the first approx. 10 cm of the adhesive bead. If material is left in the cartridge leave the static mixer attached. For further use of the product, simply remove the mixer and install a new one.

Curing:

TEROSON EP 1401 cures without additional exterior heat only by chemical reaction after mixing component A and B at room temperature. The curing time depends on the material temperature, which is influenced by room temperature and reaction heat. The more TEROSON EP 1401 is applied, the higher is the reaction heat. For accelerated curing it is recommended to use a heat source (convection oven, infrared or similar).

Cleaning:

Cured adhesive can only be removed mechanically. Fresh, uncured material can be removed with TEROSON VR 10.

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification
Transport information
Regulatory information



Storage:

Frost sensitive	conditionally
Recommended storage temperature	15 to 25 °C
Shelf life	12 months in original packaging

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties**

expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1

